

ASA-CF

COMPOSITES FOR FDM 3D PRINTING



MATERIAL NAME

ASA-CF

COLOR

Black

PROCESS

FDM

PRODUCT DESCRIPTION

Carbon Fiber ASA is a carbon fiber reinforced composite material based on weather-resistant ASA. It has the characteristics of outdoor weather resistance, UV resistance, low warpage modification and high rigidity. It is suitable for outdoor shells, fixtures, brackets and automotive functional samples.

TYPICAL APPLICATIONS

- End-use plastic parts
- Assembly testing
- Functional prototype testing
- Mounting brackets

PRODUCT SAFETY

Thermoplastic printed parts should be handled according to normal workshop safety practices. Avoid high heat, open flames, and inhalation of fumes generated during post-processing or overheating.

PRODUCT DELIVERY & WAREHOUSING

- STORAGE**
Store parts in a dry, cool, and clean environment away from direct sunlight and high heat. Keep the material sealed before processing.
- TRANSPORTATION**
Pack parts securely to prevent warping, scratching, and impact. Protect from moisture and temperature swings during transit.

PROPERTIES OF PRINTED MATERIAL

Properties	Test Method	Value
Density (g/cm3)	ISO 1183	1.02 g/cm3
Water Absorption (%)	ISO 62	0.2%
Tensile strength (MPa)	ISO 527	XY: 34 ± 3 Z: 30 ± 4 MPa
Tensile modulus (MPa)	ISO 527	XY: 4200 ± 270 Z: 2290 ± 260 MPa
Elongation at break	ISO 527	XY: 9.6 ± 1.4 Z: 4.4 ± 0.8%
Flexural strength (MPa)	ISO 178	XY: 72 ± 5 Z: 33 ± 3 MPa
Flexural modulus (MPa)	ISO 178	XY: 3740 ± 130 Z: 1350 ± 120 MPa
Heat deflection temperature @ 0.45 MPa (deg C)	ISO 75	HDT @ 0.45 MPa: 110 deg C
Heat deflection temperature @ 1.8 MPa (deg C)	ISO 75	HDT @ 1.8 MPa: 102 deg C
Impact strength notched	ISO 179	XY: 14.0 ± 2.2 Z: 6.2 ± 1.4 KJ/m²; ISO 179 (Charpy)

Tips: Want to explore a wider range of materials? Check out <https://www.unionfab.com/materials>